

Please Re-SCAN SPECIFICATION
INCLUDES INFORMAL EX and t.

A METHOD OF MANUFACTURING AN OPTICAL FIBER HAVING
COATINGS OF DISTINCT KINDS

BACKGROUND OF THE INVENTION
The invention relates to the field of optical
fibers.

5 Several methods have been developed for covering the
core and cladding material of an optical fiber in a
coating material to confer specific properties, for
example robustness, flexibility, or protection against
hostile environments.

10 Amongst those methods, proposals have been made in
particular for a covering constituted by a first coating
portion of photocurable resin having a low modulus of
elasticity, generally having an acrylic base, and by a
15 second coating portion having a high modulus of
elasticity, generally being of the same kind as the first
coating portion, and being intimately bonded therewith.

 These photocurable resins present fast reaction
kinetics in cross-linking, enabling speeds of about
2000 meters per minute (m/min) to be obtained.
20 Nevertheless, such photocurable resins provide only a
relatively narrow range of specific properties. In
addition, since the resins need to be deposited by being
applied at relatively low temperatures, typically 90°C,
and since the temperature at which optical fibers are
25 drawn is about 1600°C, it is imperative for the uncoated
optical fiber to cool down considerably on leaving the
fiber-drawing furnace, or in other words for the distance
between the fiber-drawing furnace and the coating
apparatus to be large. Finally, the cost of such
30 photocurable resins is high.

 Proposals have also been made to apply an additional
coating, referred to as a "buffer" coating, to optical
fibers already provided with identical first and second
coating portions, the buffer coating being constituted by
35 an extruded thermotropic liquid crystal polymer (TLCP).
Such an optical fiber is described in particular in US
patents Nos. 4 778 244 and 4 906 066. That type of

8414
6/21/05

coating (or covering) enables certain specific properties of optical fibers to be reinforced, and in particular their ability to withstand external stresses induced by conditions during installation and/or use. However that is not sufficient, particularly given the wide variety of properties or characteristics that are required in numerous applications for optical fibers. In addition, the operation of adding the buffer coating takes place at a speed that is very slow, typically about 1 m/min to 10 m/min, which is very far from the usual speed at which optical fiber is manufactured.

SUMMARY OF THE INVENTION

The invention thus has the object of remedying the above-mentioned drawbacks in full or in part.

To this end, the invention provides a method of coating an optical fiber in which the material of the doped silica core and silica cladding is surrounded by a coating (or covering) constituted by a first coating portion of photocurable resin, e.g. based on acrylic, and by a second coating portion made by extruding a thermoplastic polymer. The thermoplastic polymer is mixed with an additive constituted by a thermotropic liquid crystal polymer.

The thermotropic liquid crystal polymer is preferably selected from the group constituted by at least polyesters, and in particular completely aromatic polyesters and aromatic copolyesters.

The additive and the thermoplastic polymer are preferably prior mixed hot in the selected proportions so as to constitute an alloy. The proportion of additive is not more than about 10% by weight relative to the alloy, and preferably lies in the range about 2% to about 10%, and more preferably is equal to about 5%.

The thermoplastic polymer is preferably selected from polyethylene (PE), polyamide (PA), and in particular polyamide 12 (PA 12) such as Rilsan A[®], for example ACNO TL[®] and AMMON P40TLD[®].

Bu H
6/21/05

The alloy is then preferably subsequently cooled and granulated. Thereafter the granules are preferably dried prior to being extruded, e.g. using an extruder having a tubing die.

5 The method of the invention is particularly, although not exclusively, adapted to coating optical fibers for telecommunications.

The present invention also provides an optical fiber constituted by a doped silica core and silica cladding,
10 in which said core and said cladding are surrounded by a coating constituted by a first coating portion of photocurable resin and a second coating portion of thermoplastic polymer containing an additive constituted by a thermotropic liquid crystal polymer. The optical
15 fiber is manufactured by the method of the invention.

BRIEF DESCRIPTION OF THE DRAWING
Other characteristics and advantages of the

invention appear on examining the following detailed description and from the accompanying drawing in which
20 the sole figure is a diagrammatic cross-section view of an optical fiber obtained using a manufacturing method of the invention. The drawing may not only contribute to describing the invention, but it may also contribute to defining it, where appropriate.

DETAILED DESCRIPTION OF THE INVENTION

25 The invention relates to a method of coating an optical fiber constituted by a doped silica core 1 in which light propagates, and silica cladding 2. The method consists in covering the core 1 and the cladding 2 in a coating material comprising two portions 3 and 4.

A first portion 3 of the coating (or covering)
30 surrounding the cladding 2 is made by applying a coating of a photocurable resin having a low modulus of elasticity. It is preferably an acrylic-based resin whose modulus of elasticity lies in the range about 1 megapascal (MPa) to about 10 MPa, and is more
35 preferably equal to 1 MPa.

A second portion 4 of the coating (or covering) is made by extruding a meltable thermoplastic polymer around

BuH
6/21/05

BuH
6/21/05

the layer forming the first portion 3. The polymer is selected as a function of required specific properties. By way of example, the thermoplastic polymer may be polyethylene (PE), polyamide (PA), and in particular
5 polyamide 12 (PA 12) such as Rilsan A[®] (such as, for example ACNO TL[®] or AMMON P40TLD[®] sold by ATOFINA), or any other PA 12 of equivalent grade, such as for example, Ultramid[®] sold by BASF or Vestamid[®] sold by Degussa AG.

The extrusion temperature is selected as a function
10 of the thermoplastic polymer used. Nevertheless, this temperature must be higher than the melting temperature of the thermoplastic polymer. Typically, it is possible to use temperatures lying in the range about 180°C to about 330°C. This makes it possible to reduce
15 significantly the distance needed for allowing the optical fiber to cool between the two coating operations.

The extruder is preferably fitted with a tubing die. Such a tubing die serves to provide coverings that are very fine, typically having thickness lying in the range
20 about 20 micrometers (μm) to 100 μm , but without generating high pressures that are harmful for the fiber.

Furthermore, stripping can be performed using a conventional fiber stripper (a Miller[®] stripper).

By means of this method of manufacture, the cost of
25 manufacturing optical fiber can be reduced by about 25% compared with the cost of manufacturing optical fibers in which the covering is constituted by two portions of the same kind made of photocurable resin, while obtaining a fiber having surface appearance that is equivalent, and a
30 speed of manufacture that is substantially equivalent. In addition, it is possible to obtain good concentricity without significantly increasing signal attenuation.

In order to reduce the stresses to which the thermoplastic polymer is subjected during extrusion, such
35 as, for example, shear stresses and draw-down ratio (DDR), i.e. the ratio between the section of the fiber leaving the extruder over the section of the coating, as

induced mainly by the very high manufacturing speeds, it is advantageous to include an additive therein which acts as a lubricant, so as to constitute an alloy.

It may be a fluorine-containing additive, such as, for example, polytetrafluoroethylene (PTFE) or fluorinated ethylene propylene copolymer (FEP). However it is preferable to use a thermotropic liquid crystal polymer (TLCP) insofar as fluorine-containing additives can turn out to be poorly compatible with certain thermoplastic polymers, such as for electrical PA 12, and/or to be difficult to bond to the photocurable resin constituting the first portion 3 of the coating.

The TLCP is preferably selected from polyesters, and in particular polyesters that are totally aromatic, aromatic copolyesters, and in particular Vectra (sold by Hoechst Celanese), Vectra LKX 1110[®] and Vectra A 950[®], and any other TLCP of equivalent grade including Zenite[®] (sold by E.I. Dupont de Nemours), Sumikasuper[®] and Ekonol[®] (sold by Sumitomo Chemical), Rodrun[®] (sold by Unitika), and Granlar[®] (sold by Grandmont).

The proportion of additive by weight within the alloy preferably lies in the range about 2% to about 10%. This proportion varies as a function of the type of thermoplastic polymer used and of the type of additive used. For example, it is possible to make an alloy comprising 95% PA 12 AMNO TLD[®] and 5% TLCP Vectra LKX 1110[®]. In this example, the percentages are by weight. Other examples of mixtures (or alloys) are to be found in the article by F.P. LaMantia in Liquid Crystal Polymer Blend, Technomic, Lancaster, USA, Chapter 4 (1993).

The alloy is preferably obtained hot prior to extrusion, for example using a two-screw mixer. The alloy is then cooled, preferably quickly, prior to being granulated. The granules are then preferably dried prior to being extruded as described above.

Such an alloy makes it possible, specifically, to optimize the rheological behavior of the thermoplastic

polymer and to obtain high manufacturing speeds, typically of the order of 2000 m/min. In addition, TLCP reduces the melting enthalpy of the alloy, thus making it possible to simplify the cooling apparatus significantly.

- 5 By virtue of its properties, the alloy passes from the liquid state to the solid state without requiring a large amount of heat to be extracted, thus enabling it to solidify in almost instantaneous manner.

10 The invention is not limited to the implementations of the method described above, merely by way of example, but it covers any variant that might be envisaged by the person skilled in the art within the ambit of the following claims.

15 Thus, in the above, an alloy is described made from a thermoplastic polymer and an additive, for example a thermotropic liquid crystal polymer. However, it is possible to envisage that the alloy is constituted by a thermoplastic polymer and at least two different additives, such as, for example, different thermotropic
20 liquid crystal polymers, thereby conferring specific properties thereto. It is also possible to envisage adding one or more dyes to the thermoplastic polymer with or without the additive.